

DEGA STUCCO

Resins stucco of monocomponent paste.

DESCRIPTION: Dega Stucco is a product in paste, without solvents (nontoxic), mono-component of a synthetic modified copolymeric base resins, loaded with pigments, fibrous and quartz-based lamellar charges with medium and controlled granulometry.

It is a thixotropic product and therefore it can also be used for vertical applications.

EMPLOYMENTS: the product, supplied in the various colors, is usable for the restoration, the maintenance and the improvement; for located interventions or general of old floors broken up in cement, plaster, asphalt, gres, linoleum, wood, doesn't notch the polystyrene.

For: stores, mechanical shops, sheds generally and for employments in civil housebuilding also on plasters. Dega Stucco is the base for Dega Spatolato resin floorings.

PREPARATION OF THE FUND: the surface of application must result cleaning up and dry. Possible precedents covering coverings, must have removed and brushed, as also all the incongruous parts of the support in concrete.

APPLICATION: to preventively stretch on the surface to treat a hand leading Dega Primer and leave to dry.

Apply therefore in a millimeter trimming, through the use of spatula for plasters, Dega Stucco.

When the spread out layer will be dry, we will proceed to a further trimming of end with Dega Stucco, taking care of to eliminate dribbles or superficial incongruities.

Hardened the product it proceeds to the refinement with correspondence. To this point, a monolithic smooth surface and coplanar is gotten.

It is possible to aesthetically finish up such surface employing the treatments Dega Plastic, Dega Beta, Dega Brek and Floor Plus, according to the demands of use of the dressed again part.

NOTES: not do perform in an only solution bring superior to the 3/4 mm; since being monocomponent, the process of hardening would be longer with possible formation of withdrawal little cracks to plastering again.

Possible superior amount carried over to 2/3 mm. must be effected in more resumptions.

Before applying successive coats, make sure that the underlying layer has hardened completely. Ari the rooms with the aid of ventilators if necessary.

DEGA STUCCO

TECHNICAL DETAILS:

Temperature limit of exercise	- 30°C; + 60°C
Least temperature of application	+ 5° C
Time of working	in operation to the environmental temperature about 30min
Desiccation at 20° C	out dust 30min; dry: in operation of the applied thickness, ex: 2 mm. 4 hours about
Hardening	8 hours about
Specific weight	1,6 Kg./Lt.
Consumption	it is tightly tied to the type of intervention effected on the support. For trimming middle consumption of Kg. 1-1, 200 about to the mm / sqm .
Time of stocking	8 month about at 20°C – Note: it fears the cold
Packagings	6 Kg. – 25 Kg.

The values indicated mean tests averages. What indicated about the method of use and the results obtainable with our product correspond to our experiences, without however constituting our use and responsibility. Therefore, the sale of our product is not covered by guarantee with regard of application and is carried out with the understanding that the user will determine the suitability.

Certificato:



UNI 8298

Gobetto srl - Via Carroccio, 16 - 20123 Milano, Italy
tel. +39 02 8322269 fax +39 02 89404269
gobetto@gobetto.com www.gobetto.com

C.C.I.A.A Milano n. 991513
Iscriz. n. 182471 Trib. di Milano
C.F. e Part. Iva 04018090151