

## FLEXINT U.V.

**DESCRIPTION:** Flexint u.v. is a transparent epoxy component exempt from solvents, on purpose studied for the elastic finish of floors and for objects.

**CHARACTERISTICS:** Flexint u.v. makes an elastic film of easy applicability and long pot-life. Flexint u.v. is exempt from solvents and doesn't contain reactive thinners therefore the danger of irritation, contact dermatitis are reduced to the least. Flexint u.v. permits to obtain a finish with a good retention of the color.

**WAY OF USE:** mix carefully the part A with the part B in the proportions of 100-50 (es. A Kg. 1 + B Kg. 0,5) using a mixer drill middle speed, assuring of the perfect mixed.

To apply by spatula for casting. To use the product within 30 minutes. If it requires it is possible to nebulize some *diluyente per laccatura* on the surface in the zones that introduce little bubble. Don't apply on damp surfaces or with inferior temperatures to the 15°C.

**N.B. :** is possible to color Flexint u.v. with universal pigments.

### TECHNICAL DATAS:

|                           |                                             |
|---------------------------|---------------------------------------------|
| Total Dry                 | 100%                                        |
| Consumption               | 1,20 kg./sqm                                |
| Density g/Lt              | about 1010                                  |
| Pot-life at 20°C.         | about 30 min.                               |
| Dry to the touch (20°C.)  | about 8 hours                               |
| Pedestriability           | about 24 hours                              |
| Total Polymerization      | 7 days                                      |
| Extension Breakup         | 105%                                        |
| Resistance to the bending | 1.5 N/mm <sup>2</sup>                       |
| Hardness SHORE            | 1 day= A51<br>7 days= A70                   |
| Stringiness               | 170 sec. Ford 8                             |
| Flexibility               | a 0° C. = +++<br>a -10°C.=++<br>a -20°C= ++ |
| Packaging (a+b)           | 3 kg, 6 kg, 12 kg                           |

The values indicated mean tests averages. What indicated about the method of use and the results obtainable with our product correspond to our experiences, without however constituting our use and responsibility. Therefore, the sale of our product is not covered by guarantee with regard of application and is carried out with the understanding that the user will determine the suitability.

Certificato:



UNI 8298

**Gobetto srl** - Via Carroccio, 16 - 20123 Milano, Italy  
tel. +39 02 8322269 fax +39 02 89404269  
[gobetto@gobetto.com](mailto:gobetto@gobetto.com) [www.gobetto.com](http://www.gobetto.com)

C.C.I.A.A Milano n. 991513  
Iscriz. n. 182471 Trib. di Milano  
C.F. e Part. Iva 04018090151