

DEGA GAMMA

Resiniferous transparent tricomponent formulated.

DESCRIPTION: transparent resiniferous product, without solvents, from the crystalline aspect, unscented and with good characteristics of mechanical resistance. Applicable on surfaces of various nature as consolidating primer.

EMPLOYMENTS: to dress again and to protect supports of various nature (insides and outside); cement, gres, plate, ceramics, eternit, wood, etc. Suitable for the transparent protection of DEGA and Monosint Line covering. Particularly proper to prepare deteriorated surfaces and to strengthen the supports. Indicated also for surfaces with radiant panels heating.

APPLICATION: to clean the surface to be treated.

Carefully mix the three components (A+B+C), the product he introduces amber, but desiccating becomes transparent.

Now apply to roll or brush within 1 hous from the mixing.

Consumption 0,300 kg / sqm. in two hands.

TECHNICAL DETAILS:

Temperature limit of exercise	-25°C. +60°C.
Temperature of application	+18°C.+30°C.
Time of use after the miscelazione of the components at $+20^{\circ}$ Cs.	1h. about
Dessiccation	12-24h. in base to the temperature
Time for the sovra-application	24h. about.
Hardening complete	48h. about.
Dosing	Comp. A 1 Kilo. Comp. B 1,70 Kilo. Comp. C 1,70 Kilo.
Application	brush, roll, spray
Surrender for every hand	6/8 sqms. with 1 Kilo. of mixture in operation to the absorption of the support.
Time of stocking at +20°C. about.	12 mounth about.

The values indicated mean tests averages. What indicated about the method of use and the results obtainable with our product correspond to our experiences, without however constituting our use and responsibility. Therefore, the sale of our product is not covered by guarantee with regard of application and is carried out with the understanding that the user will determine the suitability.

